

BST Elastomers Co., Ltd.

175 Sathorn City Tower 22nd Fl., South Sathorn Road, Tungmahamek, Sathorn, Bangkok 10120

Tel (662) 679-5120 Fax (662) 679-5119

<http://www.bste.co.th>

Specification of BSTE SBR1723

(Spec. Code : BSTE-STD-012)

Technical Data Sheet

Chemical Identification

Oil Extended Emulsion Styrene Butadiene
Rubber (E-SBR)

Product Characteristic

RAW POLYMER

	Unit	Specification Value		Test Method
		Minimum	Maximum	
Volatile Matter	%	-	0.50	ASTM D5668-09
Ash Content	%	-	1.50	ASTM D5667-95 (Reapproved 2010)
Soap Content	%	-	0.50	ASTM D5774-95 (Reapproved 2009)
Organic Acid	%	4.20	6.20	ASTM D5774-95 (Reapproved 2009)
Bound Styrene	%	22.5	24.5	ASTM D5775-95 (Reapproved 2009)
Oil Content	%	25.8	28.8	ASTM D5774-95 (Reapproved 2009)
Raw Mooney Viscosity	MU	43	53	ASTM D1646-07 (Reapproved 2012)
ML1+4@100°C (Massed Method)				

COMPOUND PROPERTIES

Compound Mooney Viscosity	MU	55	65	ASTM D1646-07 (Reapproved 2012)
ML1+4@100°C				
Tensile Strength @ 145°C, 35 min	MPa	19.1	-	ASTM D412-06a (Reapproved 2013)
Elongation at Break @ 145°C, 35 min	%	480	-	ASTM D412-06a (Reapproved 2013)
300% Modulus@145°C				
25 minutes	MPa	6.7	11.5	ASTM D412-06a (Reapproved 2013)
35 minutes	MPa	7.9	12.7	ASTM D412-06a (Reapproved 2013)
50 minutes	MPa	9.0	13.8	ASTM D412-06a (Reapproved 2013)

COMPOUND RECIPE (ASTM D3185)

	Parts
Raw SBR1723	137.50
HAF Black (IRB#7)	68.75
Zinc Oxide	3
Stearic Acid	1
Accelerator (TBBS)	1.38
Sulfur	1.75

Compounding condition : 6 inch Two Roll Mill